测 试 报 告

报告编号： B3D826060B3C6D0R9097

签发日期： 2026-09-03

委托单位： 中材技术服务（北京）有限公司

地　　址： 北京市朝阳区望京北路 16 号

样品名称： 窗膜

型号： XM-35

生产日期： 2026-08-21

样品来源（获取方式）： 送样

样品接收日期： 2026-08-26

测试日期： 2026-08-26～2026-09-02

测试类别： 委托测试

编制人：朱琳　　审核人：张丽丽　　批准人：[illegible]

谱尼测试集团上海有限公司

————本页以下空白————

谱尼测试集团上海有限公司　电话：021-64851999
公司地址：上海市松江区施园路 288 号 1 幢 4 层 A 区
测试地址：上海市松江区施园路 288 号

测 试 报 告

报告编号： B3D826060B3C6D0R9097

签发日期： 2026-09-03

声 明
Statement

1.本报告无检验检测专用章、报告骑缝章和批准人签章无效。
This report is invalid without special seal for inspection and test, cross-page seal and signature of the approver.

2.本报告页面所使用“PONY”、“谱尼”字样为谱尼测试集团的注册商标，其受《中华人民共和国商标法》保护，任何未经本单位授权的擅自使用和仿冒、伪造、变造“PONY”、“谱尼”商标均为违法侵权行为，本单位将依法追究其法律责任。
The words "PONY" and "谱尼" used in this report page are the registered trademarks of Pony Testing International Group, which are protected by the Trademark Law of the People's Republic of China. Any unauthorized use, counterfeiting, forging or altering of the trademarks of "PONY" and "谱尼" without the authorization of us is an illegal infringement, and we will investigate their legal liabilities according to law.

3.委托单位对报告数据如有异议，请于报告完成之日起十五日内(初级农产品报告请于报告收到之日起五个工作日内)向本单位书面提出复测申请，同时附上报告原件并预付复测费。
If the applicant has any objection to the report data, please submit a written application for retesting to us within 15 days after the completion of the report (for the report of primary agricultural products, submit a written application for retesting to the unit within 5 working days after the receipt of the report), with the original report attached and the retesting fee prepaid.

4.委托单位办理完毕以上手续后，本单位会尽快安排复测。如果复测结果与异议内容相符，本单位将退还委托单位的复测费。
After the applicant completes the above procedures, we shall arrange the retesting as soon as possible. If the retest result is consistent with the objection, we will refund the retest fees.

5.不可重复性或不能进行复测的实验，不进行复测，委托单位放弃异议权利。
If the experiment cannot be repeated or cannot be retested, no retest shall be conducted, and the applicant shall waive the right of objection.

6.委托单位对送检样品的代表性和资料的真实性负责，否则本单位不承担任何相关责任。
The applicant is responsible for the representativeness of the commissioned samples and the authenticity of the documents, otherwise we do not assume any relevant responsibilities.

7.本报告未加盖检验检测资质认定标志，委托单位仅用于科研、教学、内部质量控制等活动使用，和/或不在本单位资质认定范围内，仅供内部参考，不具有社会证明作用。本报告仅对所测样品的测试结果负责，对于测试数据的使用、使用所产生的直接或间接损失及一切法律后果，本单位不承担任何经济和法律责任。
This report without CMA is only used for scientific research, teaching, internal quality control by the applicant, and/or not within the scope of ours CMA, for internal reference only, does not have social proof function. This report is only responsible for the test results of the tested sample. We do not assume any economical or legal liability generated from direct or indirect usage of the test report.

8.本单位有权在完成报告后按规定方式处理所测样品，除客户特别声明并支付样品管理费，所有超过标准规定时效期的样品均不再做留样。
We have the right to dispose the tested sample after approval of the test report. Unless the applicant specifically declares and pays the sample management fee, all samples beyond the validity period specified in the standard will not be retained.

9.本单位保证工作的客观公正性，对委托单位的商业信息、技术文件等商业秘密履行保密义务。
We assure the objectivity and impartiality of the test, and fulfills the obligation of confidentiality for applicant’s commercial information, and technique document.

10.本报告私自转让、盗用、冒用、涂改、未经本单位批准的复制(全文复制除外)或以其它任何形式的篡改均属无效，本单位将对上述行为严究其相应的法律责任。
Any unauthorized transfer, appropriation, falsification, alteration, copying (except full text copying) or alteration in any other form of this report without the approval of us shall be invalid. We shall strictly investigate the corresponding legal liability for the aforesaid behavior.

****

▲防伪说明(Anti-counterfeiting Instructions):

1.报告编号是唯一的；
The report number is unique.

2.扫描报告首页下方二维码，即可查询报告真伪。
Scan the QR code below the first page to check the authenticity of the report.

****

————本页以下空白————

测 试 报 告

报告编号： B3D826060B3C6D0R9097

签发日期： 2026-09-03

测试结果汇总：

序号	样品编号	测试项目	测试依据	限值依据	结论
1	B3C6D0R9097	雾化性能	Q/MA T5510-2021	Q/MA P3111-2021	符合

备注 1：符合：达到标准要求；不符合：未达到标准要求；/：只提供结果，不下结论。
备注 2：N.D.表示未检出（小于方法检出限）。

样品照片：




B3C6D0R9097-包装



B3C6D0R9097-样品正面



B3C6D0R9097-样品反面



B3C6D0R9097-取样部位

————本页以下空白————

测 试 报 告

报告编号： B3D826060B3C6D0R9097

签发日期： 2026-09-03

雾化性能

试验数量	2			
试验方法(详细参数)	样品取样量	Ø80mm（贴铝箔测试）	样品干燥时间	24h
	加热温度	100℃	加热时间	16h
	冷凝温度	21℃	铝箔干燥时间	4h
试验起止日期	2026-08-31~2026-09-02			
试验室环境	(23±2)℃、(50±10)%RH			
试验地点	上海市松江区施园路 288 号			
实验前样品检查	样品完好			
试验工程师	郭志友			
方法差异	无差异			

试验结果

样品编号	单位	方法检出限	目标要求(评定依据)	试验结果			结果判定
				平行样 1	平行样 2	平均值	
B3C6D0R9097	mg	0.20	≤2	N.D.	N.D.	N.D.	合格

备注 1：铝箔表面现象：铝箔表面无明显现象
备注 2：DOP 质控结果：平行样 1=4.96mg；平行样 2=4.87mg；
DOP 合格范围：(4.90±0.25)mg。

设备信息

试验设备	设备厂牌	设备型号	设备编号	有效日期
电子分析天平	梅特勒-托利多	XSR 105	B3-IE229-41	2027-05-21
雾化仪	赛默飞世尔科技	PC-201	B3-IE324-07	2027-06-07
雾化仪	赛默飞世尔科技	PC-201	B3-IE324-08	2027-06-07
电子天平	梅特勒-托利多	PL602E/02	B3-IE922	2027-06-07


————本页以下空白————

测 试 报 告

报告编号： B3D826060B3C6D0R9097

签发日期： 2026-09-03

测试照片

<table>
<tr><td>
</td><td>
</td></tr>
<tr><td>测试前</td><td>测试中 (1)</td></tr>
<tr><td>
</td><td>
</td></tr>
<tr><td>测试中 (2)</td><td>测试后</td></tr>
</table>

————报告结束————